| | | | Installation InstructionsPolyglass Split Repair for 10 Stud APT, Blueline, Environ, Weaver or Diversified PenetrationsPrepare all Surfaces: All surfaces to be bonded should be prepared prior to Completing the installation steps below.Warning: Failure to follow each step will void the warranty and may result in premature failure of the penetration fitting. Adhere to the following general instructions for each step of the installation.Bonding to Poly & FRP surfaces: Clean and sand (rough up) sump surfaces with CH-DBC II. Remove all gel coat on all fiberglass surfaces. Apply CH-DEB to all surfaces to be bonded both the fitting and sump wall.Cleaning: Spray all surfaces to be bonded with CH-DBC II Cleaner and allow to air dry. Excess cleaner may be wiped off with a clean dry cloth. | | |
|---|--|--|---|--|--|
| PG-S II 10 File Products File Products Manufacturing Inc. | | 10 | | | |
| | | 10 | | | |
| | | Weaver Products | | | |
| | PG-S II Po | lyglass Repair Kits | are used to Repair Studded Penetration Fittings. | | |
| N | lote: Most Studded Per | netrations that are the same size | e (4 stud, 8 stud,10 stud & 12 stud) use the same hole patterns. OPW Penetrations however use a different hole pattern | | |
| | The Boot shown is see have a boot that is see plate. To Repair: Remove the Metal Ri Cut off the Existing bo | , Blueline or Weaver Penetrat aled to the sump exterior. So aled to the interior wall, und ng (slide it back over the exi pot. le in the sump exposed to th | me manufacturers ler the metal stud sting pipe) | | |
| | 5.2 5.2 | | | | |
| tep 3 | Clean Polyglass Ring | with CH-DBC II and apply Ep | oxy | | |
| | Spray with CH-DBC II. Polyglass Ring approv | Wipe or air dry. (fitting and s kimately equally between the to Bonding surfaces and spre | sump) Cut the Stud Holes. | | |

Step 4

Install PG-S II Bonding Ring over Existing studs.

Wrap split Polyglass Ring around the pipe and slide over existing studs.

Step 5

Re-install Metal Plate

.

Replace Metal Ring (Removed earlier) over studs and install new ¼-20 Flange nuts, supplied in kit. Snug plate to the polyglass ring using the flange nuts.

Step 6

Open both cans and add the contents of the smaller can of hardener (Part B) to the large can of resin (Part A) and stir with the wooden stir stick provided.

When properly blended, the DEB epoxy is ready to cure. When using on vertical surfaces allow a few minutes to "set up" sufficiently to keep Epoxy from running. Use a spatula or other item to apply the DEB epoxy.

WARNING: MIX CAREFULLY TO ENSURE THE EPOXY IS WELL CATALYZED.

Step 7

Fill gap with CH-DEB Epoxy

Fill the gap between the PG-S II Series bonding ring, and the pipe with the CH-DEB epoxy.

Step 8

Paint with CH-DBF II

Paint 1/2" beyond the repair on both the sump wall and the pipe to complete installation.

Hydrostatic test may be performed 1 Hour after Painting.

Tools Required

•Sanding Tool (for sump walls)

·CH-DAG III Applicator Gun

·CH-DSM III Static Mixers (additional)

·Box Knife for Cutting Polyglass Ring

| Pipe Size | ML | OZ |
|--------------|----|------|
| 3" Flex Pipe | 70 | 2.4 |
| 3" FRP | 97 | 3.3 |
| 4" Flex Pipe | 44 | 1.5 |
| 4" LCX | 40 | 1.35 |
| 4" Corr duct | 44 | 1.5 |

OZ = Ounces for Bulk applications



| • DEIK-13 Installation Kit: |
|-----------------------------|
| •1-50ml CH-DBF II |

- Polysulfide Paint
- 1-50ml CH-DEB Epoxy
- •1-13oz CH-DEB-BULK Epoxy
- 1-Each Spatula, Brush,
- Gloves, Stir stick,

Cleaner

- •1-CH-DSP-Stick Super Putty •1-CH-DBC II - Aerosol
- installation instructions







